

## Product Specification Sheet

# JM-7108

**Product Description:** JM-7108 is a non-asbestos compressed sheet product. Its composition is comprised of environmentally friendly aramid fiber, nitrile rubber binder, and inorganic fillers. The product has well balanced mechanical properties with excellent sealability against oil and good crush resistance. It was originally designed for use in engines of farming equipment and is now widely used for agriculture equipment applications. The application temperature range of this product is -40°C ~ 300°C.

Product Gauge: 1.0±0.1 mm. (Other thickness can be made upon requested)

### Property Specifications

Property	Unit	Value	Test Method
Density	g/cm <sup>3</sup>	1.6 -2.0	ASTM F1315
Tensile Strength, AMD	MPa	≥ 8.0	ASTM F152
Compressibility (34.5 MPa)	%	≥ 12	ASTM F36
Recovery	%	≥ 35	ASTM F36
Fluid Immersion, #903 Oil (150°C ×5h)			ASTM F146
Weight Change	%	≤ 23	
Thickness Change	%	≤ 20	
Fluid Immersion, Fuel B (室温 21-30 °C ) ×5h			ASTM F146
Weight Change	%	≤ 20	
Thickness Change	%	≤ 20	

Remark: The description and performance data provided herein constitutes material specifications for quality control purposes, but do not imply suitability for use in a specific application. Your specific application should not be undertaken without independent study and evaluation for suitability. Failure to select a proper sealing product may result in either property damage or personal injury. For questions regarding specific applications, contact Junma Sealing Technology, Inc. for assistance.